

Dulux Weathershield Low Sheen

NZ_DD02644






Part A	54L LINE
---------------	----------

Description
DULUX WEATHERSHIELD® has been specially designed to provide a tough, hardwearing finish that provides protection from all weather conditions. Formulated with MaxiFlex Technology to expand and contract with the surface, Dulux guarantees Weathershield won't peel flake or blister for as long as you live in your home (15 year commercial warranty provided it is applied according to an approved written Dulux Duspec Specification).

Features
<ul style="list-style-type: none"> • Tough & Hardwearing • Self Priming on most surfaces • Helps resist mould, dirt and stains • Long lasting colour • UV protections

Uses
Exterior surfaces such as timber, bricks, concrete, fibre cement board, masonry, Zinalume steel, Colorbond, Colorsteel, galvanized iron and suitably prepared steel and wrought iron.

Performance Guide			
Weather	Excellent resistance to weathering with very low level of chalking, colour change and dirt pick up.	Salt	For galvanised iron within 1 km of the sea (or other salty areas), prime with Dulux Precision All Metal Primer
Heat Resistance	Softens at temperatures above 70°C	Water	Resists prolonged rain and condensation.
Solvent	Sensitive to aromatic hydrocarbons, alcohols and ketones.	Abrasion	Good resistance to abrasion.

Typical Properties																											
Gloss Level	5-20 at 60°	Thinner	Water																								
Colour	A full range of colours from an extensive range of white and coloured bases.																										
Dulux Colour Base	BLACK, BLUE BASE, BOLD YELLOW, DEEP, EXTRA BRIGHT, ORANGE, TRUE RED, ULTRA DEEP, VIVID WHITE																										
Components	1	Number Of Coats	2 or 3																								
Toxicity	Lead free. Dry film is non-toxic.	Sanding Properties	Good																								
Touch Dry	20 Minutes																										
Clean Up	 Water																										
Clean Up Description	Clean all equipment with water																										
Application Method	    Air Spray Airless Spray Brush Roller																										
Application Conditions	<table border="0"> <tr> <td style="text-align: center;">Solids By Volume</td> <td style="text-align: center;">38</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td></td> <td></td> <td style="text-align: center;">65</td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td></td> <td></td> <td style="text-align: center;">25</td> </tr> <tr> <td>Recoat Time (min)</td> <td style="text-align: center;">2 hr</td> <td style="text-align: center;">Indefinite</td> <td></td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td></td> <td></td> <td style="text-align: center;">15.2</td> </tr> </table>			Solids By Volume	38				Min	Max	Recommended	Wet Film Per Coat (microns)			65	Dry Film Per Coat (microns)			25	Recoat Time (min)	2 hr	Indefinite		Theoretical Spread Rate (m ² /L)			15.2
Solids By Volume	38																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)			65																								
Dry Film Per Coat (microns)			25																								
Recoat Time (min)	2 hr	Indefinite																									
Theoretical Spread Rate (m ² /L)			15.2																								

Application Guide

Surface Preparation	<ul style="list-style-type: none"> PREVIOUSLY PAINTED SURFACES Test if surface is sound by cutting a small X through the existing paint with a sharp blade, press cellulose tape firmly across the cut and then rip off the tape. If the paint comes off, it is unsound and should be removed. Repeat at random in a number of areas to test the surface. Clean with Dulux Prep Wash. Scrape off all loose and flaking paint. Fill any cracks or holes with a suitable exterior filler. Dulux recommends Selleys products. Sand all surfaces to a flat finish and remove greyed timber. Dust off. PRE-PRIMED TIMBER/FIBRE CEMENT Preparation can vary depending on the quality and condition of the substrate. For help and advice call NZ 0800 800 424 BARE (UNPAINTED) TIMBER Fill nail holes with a flexible, exterior grade wood filler. Dulux recommends Selleys products. Sand all dressed timber and remove greyed timber. For some bases on hardwoods, apply 1 coat of Dulux 1Step prepcoat for improved resistance to cracking. BARE BRICK, MASONRY, FIBRO & FIBRE CEMENT BOARD Unpainted masonry surfaces should be cured for 28 days before painting. Ensure surface is clean and clear of any loose sand or cement. Fill holes with grouting cement. Wash down with water using a stiff brush to remove all loose material. To remove any efflorescence (white salts) wipe down with a 5% solution of acetic acid (white vinegar). Hose down and allow to dry. Wash with a bleach solution and/or demossing chemical to remove mould or moss, then hose down. GALVANISED IRON Clean with a scouring pad and Selleys Sugar Soap solution. Thoroughly hose off. For surfaces within 1km of the sea, and some bases, apply one coat of Dulux Precision All Metal Primer. COLORBOND & COLOURSTEEL Preparation requirements can vary depending on the condition of the substrate. For help and advice call NZ 0800 800 424. ZINCALUME STEEL Clean with Selleys Sugar Soap solution. Thoroughly hose off. For surfaces within 1km of the sea, and some bases, apply one coat of Dulux Precision All Metal Primer. STEELWROUGHT IRON Remove all rust by scraping, sanding or wire brushing. Apply 2 coats of Dulux Precision All Metal Primer.
Application Procedure And Equipment	<ul style="list-style-type: none"> Brush, roller, conventional and airless spray Stir contents thoroughly before and during use with a broad flat stirrer, using an upward lifting action. Apply two generous coats of Weathershield. Apply three coats on all unpainted surfaces. Primer may be required on some substrates (see surface preparation). Some colours may require more than 2 top coats and or the use of a tinted undercoat. This is particularly relevant when using bright or high chromatic coloured paints (e.g. colours derived off True Red, Bold Yellow, Orange, and Extra Bright base) or when painting over existing dark colours. Under hot or windy conditions, up to 100ml DULUX Hot Weather Thinner may be added per litre to assist application. BRUSH/ROLLER Soak brush and roller in water before starting and use while still slightly damp. Use a short nap roller. Avoid excessive brushing or rolling back into paint which has been drying some minutes. AIRLESS & CONVENTIONAL SPRAY Suitable for application by all standard spray equipment. If necessary thin with up to 100ml/litre of water to aid atomisation.

Health And Safety

MSDS Number	DLXNZLEN003376	Using Safety Precautions	For detailed information refer to the product label and the current Material Safety Data Sheet available through Dulux Sales and Customer Service offices.
MSDS Link	https://go.lupinsys.com/duluxgroup/harms/pm/7b5efd9fcac7ed73d13dc750a348169d-published/attachment/nz-sds.pdf		
Health Effects	Splashes to the eye may cause eye irritation. When spraying, inhalation of mists may produce respiratory irritation.	Protective Equipment	Wear eye protection and when spraying wear a suitable mask.
Disposal	Do not contaminate stormwater with product or product washings. Do not pour product down the drain. Unwanted product should be brushed out on newspaper, allowed to dry and then disposed of via domestic waste collection. Empty containers should be left open in a well ventilated area to dry out. When dry, recycle the container via recycling programmes. Disposal of empty paint containers via recycling programmes may differ between local authorities. Check with your local council first.		

In the case of emergency, please call 0800 734 607

Precautions And Limitations

All preparation and painting must conform to AS2311: The Painting of Buildings.
 Do not apply at air or surface temperatures below 10C or when temperatures may fall below 10C during the drying period. In summer paint on the shady side of the building. If conditions are hot and windy, cool the surface by hosing with water and paint the cool damp surface. Do not apply to roofs or surfaces used for the collection of drinking water. In normal conditions, 7 days curing is required to develop full hardness and resistance properties. Occasionally when dew or condensation forms on dried film, a slight milky deposit will be observed on the film. This is quite normal and does not impair the performance - simply hose or wipe it off with a damp rag.

Caution - Check with your substrate manufacturer before painting colours of LRV<40

Transport And Storage

Pack A	54L LINE	Shipment Name	Not dangerous goods.; No special transport requirements.
Size		Weight	
1L		1.4kg	
2L		2.8kg	
4L		5.5kg	
10L		13.5kg	
15L		20.2kg	
Flash Point	NA	UN Number	NA
Dangerous Goods Class	NA	Package Group	NA

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.
 DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (New Zealand) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road NZ ACN 133 404 118